

**DEXRON® ASTM D7043 Modified  
Report Forms  
Form 1**

Formulation Code							
Formulation Code							
SID	SponsorCode	Modification	Blend	Method	Count	Lab	Pump System

Blended Sample Testing Information <sup>A</sup>			
Candidate Percentage			Other Percentage
Other Fluid ID			

<sup>A</sup> If not a Blended Sample then report 100% Candidate Percentage, 0% Other Percentage, and “None” for Blend Fluid ID.

Test Identification			
Sponsor			
Sponsor In-House Number			
Lab In-House Number			
Alternate Code			
Test Number <sup>B</sup>			
Pump System		Run Number	
Start Date		Start Time	
EOT Date		EOT Time	

<sup>B</sup>Test Number = Pump System– Run Number

Test Validity Statement	
This test has been conducted in a valid manner – YES or NO	
Test Laboratory	
Signature	
Typed Name	
Title	

**DEXRON® ASTM D7043 Modified**

**Pass/Fail Results**

**Form 2**

Formulation Code	
Test Number	

<b>Pass/Fail Result</b>	
Parameter	Mass Loss - mg
Total Mass Loss ( Rings + Vanes)	

<b>Test Conditions</b>		
Parameter	Average	Specification
Pump Inlet Temperature - °C		80°C ± 3 °C
Pump Speed - rpm		1200 rpm ± 60 rpm
Pump Outlet Pressure - mPa		6.9 mPa ± 0.3 mPa
Fluid Volume – L		11.356 ± 0.5L

<b>Additional Information</b>		
Test Length - h		100 h Required

<b>Part Measurements</b>			
Part	Initial - g	EOT - g	Loss - mg
Ring Weight			
Vanes Weight			
Total			

<b>Comments</b>